

Prince & Izant Company

12999 Plaza Drive

Cleveland, Ohio 44130

T: 216-362-7000

F: 216-362-7456

princeizant.com



Pt80/Ir20

TECHNICAL DATA

NOMINAL COMPOSITION	Platinum	80.0% ± 1.0
	Iridium	20.0% ± 0.5
	Total Impurities	0.2% max.
	Total Platinum Group (Pd, Rh, Os, Ru), Au	0.1% max.
	Total Other Impurities (Including those listed below)	0.1% max.
	Lead	0.01% max.
	Antimony	0.01% max.
	Bismuth	0.01% max.
	Tin	0.01% max.
	Arsenic	0.01% max.
	Cadmium	0.01% max.
	Zinc	0.01% max.
	Iron	0.01% max.
	Mercury	0.01% max.
	Nickel	0.007% max.
Other elements (each)	0.02% max.	
PHYSICAL PROPERTIES	Color	Silver
	Melting Point °F (°C)	3325 (1830)
	Density (g/cm ³)	21.68
	Electrical Resistivity (μΩ*cm @ 0°C)	
	Fully Annealed:	31.0
	Tensile Strength @ 0.010" diam. (KSI)	
	Work hardened:	190 – 210
	Fully Annealed:	90 – 110
	Elongation @ 0.010" diam. (%)	
	Work hardened:	<2
Fully Annealed:	>10	
Temp. Coeff. Of Resistance (0-100°C)		
Work Hardened:	0.0007	
Fully Annealed:	0.0008	
USES	Pt80/Ir20 is typically utilized for in-vivo applications such as marker bands, feedthrough pins and micro-coil components.	
SPECIFICATIONS	Pt80/Ir20 alloy conforms to: ASTM B684 / B684M – 22	
AVAILABLE FORMS	Wire, rod, strip, seamless tubing, machined components.	

NOTE:

DISCLAIMER

The information and recommendations contained in this publication have been provided without charge & compiled from sources believed to be reliable and to represent the best information available on the subject at the time of issue. No warranty, guarantee, or representation is made by the Prince and Izant Company, Inc. as to the absolute correctness or sufficiency of any representation contained in this and other publications; Prince and Izant Company, Inc. assumes no responsibility in connection therewith; nor can it be assumed that all acceptable safety measures are contained in this (and other publications, or that other or additional measures may not be required under particular or exceptional conditions or circumstances.