

Prince & Izant Company

12999 Plaza Drive
Cleveland, Ohio 44130
T: 216-362-7000
F: 216-362-7456
princeizant.com



SILVERPHOS 15 (BCuP-5)

TECHNICAL DATA

NOMINAL COMPOSITION	Copper	80.0% ± 1.0
	Phosphorus	5.0% ± 0.2
	Silver	15.0% ± 0.5
	Other Elements, Total	0.15% Max
PHYSICAL PROPERTIES	Color	Gray
	Solidus	1190°F (643°C)
	Liquidus	1475°F (801°C)
	Recommended Brazing Temperature	1525-1575°F (829-857°C)
	Density (lbs./in³)	0.31
	Specific Gravity	8.44
	Electrical Conductivity (%IACS)	9.90
	Electrical Resistivity (Microhm-cm)	14.4
USES	<p>Silverphos 15 was developed primarily for use on copper, but its use has extended to other nonferrous copper base alloys. It is used extensively on refrigeration units, air conditioning apparatus, electrical conductors, copper and brass pipe fittings, and other copper and brass equipment.</p>	
	<p>Silverphos 15 is a copper rich, filler metal that is self-fluxing on copper by virtue of its phosphorus content. The self-fluxing property of this filler metals is effective on copper only. With copper-base alloys, such as brass or bronze, the joints should be fluxed. Silverphos 15 should not be used on nickel-base and iron-base alloys, as the phosphorus reacts with the nickel or iron to form brittle compounds at the interface of the joints.</p> <p>Silverphos 15 has a strong tendency to liquate (separation into low and high melting constituents) if heated slowly through its melting range, as normally occurs in furnace brazing. This results in leaving a “skull” of un-melted alloy behind which may be objectionable from the standpoint of appearance. In furnace brazing it is preferable to pre-place the alloys inside the joint where the skull is not visible.</p> <p>Normally the corrosion resistance of Silverphos 15 is of the same order as copper, but under certain conditions it may corrode more rapidly. Silverphos 15 should not be used where the joints are exposed to sulfur compounds, especially in gasses or oils at temperatures above normal room temperature. As the corrosion by sulfur is cumulative, even very small percentages will eventually cause failure of the joint by disintegration. Exposure to pressured steam can also result in accelerated corrosion.</p>	
BRAZING CHARACTERISTICS		
PROPERTIES OF BRAZED JOINTS	<p>The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal.</p>	

SPECIFICATIONS

Silverphos 15 alloy conforms to: American Welding Society (AWS) A5.8/A5.8M BCuP-5, Unified Numbering System (UNS) C55284 and ISO 17672 CuP 284

AVAILABLE FORMS

Wire, engineered preforms, specialty preforms per customer specification, powder and paste

Individuals requiring further information and Engineering Specification Documents may wish to contact the Engineering Society for Advanced Mobility, Land Sea Air and Space, The Society of Automotive Engineers <http://www.sae.org/> (SAE AMS) or The American Welding Society (AWS) <http://aws.org/>

NOTE:**DISCLAIMER**

The information and recommendations contained in this publication have been provided without charge & compiled from sources believed to be reliable and to represent the best information available on the subject at the time of issue. No warranty, guarantee, or representation is made by the Prince and Izant Company, Inc. as to the absolute correctness or sufficiency of any representation contained in this and other publications; Prince and Izant Company, Inc. assumes no responsibility in connection therewith; nor can it be assumed that all acceptable safety measures are contained in this (and other publications, or that other or additional measures may not be required under particular or exceptional conditions or circumstances.